

# PRODUCT DATA SHEET

010 00128

**PRODUCT DESCRIPTION:** Flexible Magnetic

**STANDARD THICKNESS:** 0.75mm (+/- 0.03mm)

**STANDARD WIDTH:** 620mm (+3mm/-1)

**STANDARD LENGTH:** 30M (+0.6M/-0)

**GROSS WEIGHT:** 55 KG

## MAGNETIC PROPERTIES

Maximum Energy Product: 0.45 – 0.55 MGOe

Remanence: 1600 – 1900 G

Coercivity: 1200 – 1500 Oe

Intrinsic coercivity: 2200 – 2500 Oe

Pole width: 2.0 mm

Magnetic pull: 28 g/cm<sup>2</sup>

## PHYSICAL PROPERTIES

Flexibility: can be wrapped around a rod with a 12mm radius at 20°C without cracking

Specific Gravity: 3.5 to 3.7 g/cm<sup>3</sup>

Cutting: Scissor cutting, knife-cutting, die-cutting and slitting can be done with ease

## TEMPERATURE RESISTANCE

End-use temperature range: - 30°C / + 55°C

Short term resistance: + 65°C

## MATERIAL PROPERTIES

The magnetic sheeting has a UV hardened coating on the magnetic side

### Storage:

The material should be stored horizontally. Avoid sunlight and keep temperature between 10 and 30 degrees Celcius.

Sanders Group:

Industriepark 3

5663 PG

Geldrop

The Netherlands

[www.sandersgroup.eu](http://www.sandersgroup.eu)

Magnetic Solutions Ltd.

Unit 15c Tinsley Industrial Estate

Shepcote Lane

Sheffield

S9 1TH

United Kingdom

[www.magnetic-solutions-ltd.co.uk](http://www.magnetic-solutions-ltd.co.uk)

Aiman GZ

Parque Empresarial Neinor Henares

Edificio 7 – Nave 14

28880

Meco – Madrid

Spain

[www.aimangz.es](http://www.aimangz.es)



# SANDERS