

## TECHNICAL DATA SHEET

### Blockout CA6 - 610 g

Item	Unit	Value		Test Method
<b>Base Fabric</b>	Denier	1000DX1000D		(Domestic yarn) 100%PES
<b>Construction</b>	Weaving/inch	9x9		/
<b>Weight of fabric</b>	Gsm/m2	75±5		DIN53352 BS3424 Method5B
<b>Weight of PVC</b>	Gsm/m2	535±5		DIN53352 BS3424 Method5B
<b>Total weight</b>	Gsm/m2	610±10		DIN53352 BS3424 Method5A
<b>Thickness</b>	mm	0.48±0.02		DIN EN ISO 2286-3
<b>Width</b>	cm	102---500		/
<b>Tensile Strength</b>	N/5cm	Warp	1350	DIN53352 BS3424
		Weft	1200	
<b>Tearing Strength</b>	N	Warp	245	DIN53356 BS3424
		Weft	185	
<b>Adhesion</b>	N/5CM	60		DIN53357 BS3425 Method9B
<b>Temperature Resistance</b>	°C	-20~70		DIN53357 BS3425 Method10
<b>Lacquering</b>	None			
<b>Flammability</b>	We can be applied for: B2, DIN75200			
<b>LOW CADMIUM &amp; HEAVY METALS</b>	We can be applied for: EN71-3			
<b>Conclusions and Announcements</b>	<p>Declaration: Please choose the products suitably according to relative provisions or industrial standards. The producer bears the responsibility for the specified technical and performance data on this page only and is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)</p> <p>Remarks: "M" represents Matte surface.</p>			