

TECHNICAL DATA SHEET

DigiPrint PET Blockout

| Item | Unit | Value | Test Method |
|---------------------------------------|---|---|-----------------------------|
| Support Base | Polyethylene Terephthalate (PET) | | |
| Thickness of PET | Micron | 125 | / |
| Coating | WHITE PVC ON TOP AND BACK SIDES | | |
| Total weight | Gsm/m2 | 530±20 | DIN53352 BS3424 Method5A |
| Width | m | 0.914, 1.06, 1.27, 1.37, 1.52, 1.60, 2.20, 3.20 | |
| Tensile Strength | N/5cm | Warp | 1182 |
| | | Weft | 1173 |
| Tearing Strength | N/5cm | Warp | 34 |
| | | Weft | 27 |
| Adhesion | N/5CM | 60 | DIN53357 BS3425 Method9B |
| Temperature Resistance | °C | -20~70 | DIN53357 BS3425 Method10 |
| Flammability | We can reach: B1, B2, M2, NFPA701, etc. | | |
| LOW CADMIUM & HEAVY METALS | We can be applied for : Cadmium free (EN71-3) or Reach Compliance | | |
| Ink Printability | Solvent, Eco-solvent, and UV | | |
| Advantages: | <ul style="list-style-type: none"> ◆ Super smooth surface(without base fabric). ◆ Black interlayer and double-face printing. ◆ Anti curling appearance. ◆ Excellent printing performance | | |
| Applications | Hanging graphics for exhibition, retail display, Pole banners, corporate events, etc. | | |
| Conclusions and Announcements | Declaration: Please choose the products suitably according to relative provisions or industrial standards. The producer bears the responsibility for the specified technical and performance data on this page only and is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable) | | |