RO - 400046 Cluj Napoca, str. Traian 86-88
CIF: RO 5612469; J12/1182/1994
Raiffeisen Cluj: RO68 RZBR 0000 0600 1849 3189
Capital subscris: 500.000

TECHNICAL DATA SHEET

SCRIMLESS PET GREY BACK 340G

Item	Unit	Value		Test Method
Support Base	Polyethylene Terephthalate (PET)			
Thickness of PET	Micron	100		/
Coating	PVC/Grey PVC			
Total weight	Gsm/m2	340±20		DIN53352 BS3424 Method5A
Total Thickness	mm	0.24		
Width	m	0.914, 1.06, 1.27, 1.37, 1.52, 1.60, 2.20, 250, 3.20		
Tensile Strength	N/5cm	Warp	982	DIN53354 BS3424 Method6A
		Weft	873	
Tearing Strength	N/5cm	Warp	34	DIN53356 BS3424 Method7A
		Weft	27	
Adhesion	N/5CM		60	DIN53357 BS3425 Method9B
Temperature Resistance	℃	−20～70		DIN53357 BS3425 Method10
Flammability	Can be apply for B2 and NFPA701 only			
LOW CADMIUM & HEAVY METALS	We can be applied for : Cadmium free (EN71-3) or Reach Compliance			
Ink Printability	Solvent, Eco-solvent, UV and Screen printing			
Advantages:	◆Non-curling at the edge and lay-flat appearance ◆Super smooth surface for high resolution printing. ◆Excellent printing performance. ◆Comparing to water-based inkjet media, print direct to substrate, no lamination needed.			
Applications	◆Display system, Roll-up, Pop-up, X-Banner, Scrolling banner. ◆Trade shows and Event Graphics ◆Any hanging banner and sign applications			
Conclusions and Announcements	Declaration by GLP: Please choose GLP products suitably according to relative provisions or industrial standards. GLP bears the responsibility for the specified technical and performance data on this page only. GLP is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)			