



TECHNICAL DATA

LAMINATED BLOCKOUT 480G (M)

Item	Unit	Value		Test Method
Base Fabric	Denier	840DX840D		(Domestic yarn) 100%PES
Construction	Weaving/inch	9x9		/
Weight of fabric	Gsm/m2	75±5		DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	405±5		DIN53352 BS3424 Method5B
Total weight	Gsm/m2	480±10		DIN53352 BS3424 Method5A
Thickness	mm	0.40±0.02		DIN EN ISO 2286-3
Width	cm	102---500		/
Tensile Strength	N/5cm	Warp	1350	DIN53352 BS3424
		Weft	1200	
Tearing Strength	N	Warp	245	DIN53356 BS3424
		Weft	185	
Adhesion	N/5CM	60		DIN53357 BS3425 Method9B
Temperature Resistance	°C	-20~70		DIN53357 BS3425 Method10
Lacquering	None			
Flammability	We can be applied for: B2, DIN75200			
LOW CADMIUM & HEAVY METALS	We can be applied for: EN71-3			

RO - 031301 București
Calea Vitan nr. 238, sector 3
Tel: 021.326.46.30
E-mail: bucuresti@verla.ro

RO - 400235 Cluj Napoca
Str. Corneliu Coposu nr. 41, Cluj
Tel: 0264.449.450
E-mail: cluj@verla.ro



Conclusions and Announcements

Declaration by supplier: Please choose products suitably according to relative provisions or industrial standards. supplier bears the responsibility for the specified technical and performance data on this page only. supplier is not responsible for any other liability. (The technical data on this page is calculated on average, and $\pm 5\%$ tolerance is acceptable)

Remarks: "M" represents Matte surface.