



Test Report

Determination of friction

Report-No.: 903 7250-1/Sgm

Client: Avery Dennison Materials Belgium sprl.
Bld Kennedy, Z.I. Zone B
7060, Soignies, Belgium

Order-No. (Client): -

Order-No. (MPA): 903 7250 000

Test Item: Permaflex LUV 6400

Specification Applied: [1] DIN EN 13036-4: 2011-12
Road and airfield surface characteristics – Test methods –
Part 4: Method for measurement of slip/skid resistance of a
surface – The pendulum test

Date of Receipt of Test Item 09.07.2019

Date of Test: 19.07.2019

Date of Report: 19.07.2019

Page 1 of 3 text pages

Enclosures : -

Supplements: -

Total Number of Pages: 3

Number of Reports: 2

The test results relate only to the items tested.

Publication of this report in full or partly is only allowed with written authorization by MPA University of Stuttgart.

1 Purpose of Investigation

You commissioned us with testing of friction properties of the sample “**Permaflex LUV 6400**” according to DIN EN 13036-4 [1] (dry and wet conditions). For testing the samples were fixed on a piece of parquet.

2 Testing procedure

The test was performed according to DIN EN 13036-4 [1] (accredited test according to DIN EN ISO/IEC 17025, see DAkkS-certificate D-PL-11027-04-07).

3 Results of Investigation

The following test results were obtained.


Table 1: Test results, friction of “**Permaflex LUV 6400**” on parquet according to DIN EN 13036-4 [1] (dry conditions)

testing spot no.	Friction (PTV-value)	
	longitudinal direction (dry condition)	transverse direction (dry condition)
1	112	116
2	112	117
3	113	117
4	113	116
5	113	116
Average	113	116

Table 2: Test results, friction of “Permaflex LUV 6400” on parquet according to DIN EN 13036-4 [1] (wet conditions)

testing spot no.	Friction (PTV-value)	
	longitudinal direction (wet condition)	transverse direction (wet condition)
1	26	28
2	25	26
3	25	27
4	25	27
5	25	27
Average	25	27

Prepared by



Oliver Konrad
Testing Engineer



Approved and released by



Dr.-Ing. Michael Stegmaier
Section leader