



TRISOLV BILLBOARD PAPER PRIME 135 GLOSSY

glossy 3682, 135 g/m²

Premium, glossy, blueback poster paper for billboard applications

This multi-coated, weatherproof paper with high wet-strength and a gloss finish is suitable for printing with solvent, latex and UV-curing inks. Prints impress with high colour brilliance and very good image definition. The material dries quickly even with high ink densities and displays good flatness. TriSolv Billboard Paper Prime 135 qualifies for outdoor billboard applications and displays very good resistance to scratches and good folding endurance. The opacity of the blueback ensures optimum coverage of substrates.

Advantages

- Excellent colour brilliance
- Water-repellent surface
- Opaque blueback ensures good coverage of substrates
- High scratch resistance
- FSC® certified



Technologies



General tips

- The ink amounts must be adjusted to the paper. Please reduce the single colors cyan, magenta, yellow and black (ink restrictions) and shorten the maximum amount of ink (ink limit). This will help your costs on inks and improve your drying performance.
- Please follow the recommendations of the printer and ink manufacturer. The temperature for preheating and drying the media should be checked previously to make sure you will achieve desired results.
- Pasting application: After wetting the paper should be kept in a plastic box in order to wet the paper sufficiently. We recommend to keep the TriSolv Paper wet for at least eight hours. Longer periods of time don't have any negative impact on the paper. The user is responsible for appropriate microbiological precautions.
- In the event that the paper is exposed to severe climatic conditions, or if it needs to be used for a longer period of time, lamination is recommended. It is advisable to protect the edges and corners if the billboard hoarding is regularly cleaned.
- The TriSolv Papers blue back have passed the "Klebstest" of the Swiss billboard association, Allgemeine Plakatgesellschaft (APG). The application features are confirmed.
- To maintain the high quality of the paper, it should be stored and converted in a climate of 30 – 65 % relative humidity and at a temperature of 10 – 30 °C (50 – 86 °F).

Physical data

Name	Value	Norm
Weight [g/m ²]	135	ISO 536
Thickness (paper) [µm]	150	ISO 534
Opacity [%]	> 98	ISO 2471
Gloss (85°)	68	ISO 2813
Chromaticity (D50/2°) a* M0	L*93.6 / a*1.4 / b*-6.5	ISO 13655, M0



TRISOLV BILLBOARD PAPER PRIME 135 GLOSSY
