

# DirectTex® Softimage Contrast

Fields of application

**.01 .02 .03 .04 .07**

## Specifications



599150 150



100 % polyester



ca. 160/ 252/ 320/ 505 cm  
ca. 63/ 99/ 126/ 199 inch  
other widths available on request



B-s1, d0 DIN EN 13501-1



ca. 210 g/m<sup>2</sup>  
ca. 6.8 oz/yd<sup>2</sup>



ca. 0.37mm  
ca. 370 µm



rolls  
50/ 100 m  
55/ 109 yd



length: 448.7 N  
cross: 683.6 N  
DIN EN ISO 13934-1



length: 31.4 %  
cross: 53.3 %  
DIN EN ISO 13934-1



blank: 7  
DIN EN ISO 105-B02



blank: 88.76  
DIN 5033-1



length: 0.9 %  
cross: 0.7 %  
DIN EN 14704-1



cold, ultrasonic cut

## Printing methods

print	UV	Latex	Dyesub
Inside	•		•
Outside			

## Article shrinkage (33 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,5 %	1,2 %	185
190°C	/ %	/ %	
200°C	/ %	/ %	
210°C	/ %	/ %	

## Certifications



## DirectTex® Softimage Contrast

Fields of application

.01 .02 .03 .04 .07



Ref.-Nr.: 599150 150 | Preview print sample