



RO - 400046 Cluj Napoca, str. Traian 86-88  
CIF: RO 5612469; J12/1182/1994  
Raiffesien: RO68RZBR0000060018493189

## Film APET Clear GTB 180

Poliester Transparent optical clear, 180 microni

PROPERTIES	STANDARD	VALUE	UNIT	REMARKS
Thickness	ASTM D 1593	180	$\mu$	Tolerance $\pm 7\%$
Density	ASTM D 792	1,34	$\text{g/cm}^3$	
Gloss 60°		>140	%	
Surface tension	ASTM D 2578-84	$\geq 38$	dyne/cm	
Tensile strength	ASTM D 638	$\sim 40$	$\text{N/mm}^2$	
Shrinkage Machine direction (MD) Transversal direction (TD)	ASTM D 1204	$\leq 5$ $\leq 3$	%	
Minimum sheet size		200X200	mm	Tolerance $\pm 1$ mm
Maximum sheet size		1200X1600		
Reel width		MAX 1700	mm	Tolerance - 0 / +3mm
Storage	Store for at least 24 hours in the room where the material is processed. Do not expose to direct sunlight. Storage temperature ranging between 10 and 35°C Store rolls in original packaging.			

RO - 031301 București  
Calea Vitan nr. 238, sector 3  
Tel: 0729 016 484  
E-mail: bucuresti@verla.ro

RO - 700381 Iași  
Aurel Vlaicu, nr. 87  
Tel: 0746 124 531  
E-mail: iasi@verla.ro

RO - 400235 Cluj-Napoca  
Str. Corneliu Coposu nr. 41  
Tel: 0721 242 216  
E-mail: cluj@verla.ro

[www.verla.ro](http://www.verla.ro)