

FOAMALUX Light, White



Foamalux Light is an extruded, closed cell, unplasticised PVC foam sheet. The fine, uniform, closed cell structure underlies a firm, satin surface.

Product Range

1 Toddot Hange	
Standard Sheet Sizes (mm)	Thickness (mm)
1220 x 2440	2,3,4,5,6,8,10
1560 x 3050	2,3,5,10
2050 x 3050	2,3,4,5,6,8,10

^{*}Non-standard sizes are available subject to minimum order quantities.

Application

Typical end uses of Foamalux Light:

Signage Shop Outfitting Display Digital Printing

Wall Cladding Insulation Panel
Partitioning False Ceiling
Fabrication Models
Furniture Shelving

Service Temperature

Foamalux Light PVC can be installed in a diversity of applications, with varying temperatures. The material's mechanical performance is known to remain stable in prolonged service in temperatures ranging from -20 to +60 °C.

Storage & Handling

Foamalux Light PVC foam sheets are best stored indoors under ambient warehouse conditions up to 20 °C, away from direct sunlight, in a cool dry store. Do not store indoors close to heat sources, for example, radiant heaters or boilers. Standing sheets on ends or sides should be avoided. Store flat on an even, level surface, supported at all points. No more than three pallets on stack

Installation

Applications of Foamalux Light PVC must make adequate allowance for thermal movement. Adequate clearance must be allowed if holes are drilled for fixing and in rebates of support frames.

Print Preparation

For a sheet clean and protected by film, only ionization or static brush is required. Lukewarm water and ordinary non-abrasive household detergent and a sponge or soft cloth is normally sufficient for degreasing and cleaning prior to secondary operations the following solvents are suitable: methyl alcohol or methylated spirits.

Static

Rinsing the surface with water or antistatic cleaning agent can reduce static charge. Another method is to blow down the sheet with ionised air. The effect of this treatment is short term but usually sufficient for subsequent operations



Brett Martin Ltd. pursues a policy of continuous product development and reserves the right to amend specifications without notice.

Brett Martin Ltd., 24 Roughfort Road, Mallusk, Co. Antrim, N. Ireland, BT36 4RB. Tel: +44 (0)28 9084 9999 Fax: +44 (0)28 9083 6666 E-mail: technical@brettmartin.com