

Produktdatenblatt Polarbearpaper PP protection paper

Technische Spezifikation - Technical data sheet - Fiche technique

Sorte / paper grade / type de papier:			24 g/m ²
Flächengewicht [g/m ²] substance grammage	ISO 536 Tappi T410		24 (+/-5%)
Dicke mm Thickness Épaisseur	DIN EN ISO 534:2011		0,045
Bruchwiderstand [N/15 mm] <i>breaking strength</i> résistance à la rupture	DIN ISO 1924-3 Tappi T494	l/md/sm q/cd/st	23 10
breitenbezogene Bruchkraft [kN/m] tensile strength force de rupture	DIN ISO 1924-3 Tappi T494	l/md/sm q/cd/st	1,6 0,6
Reißlänge [m] breaking length longueur de rupture	DIN ISO 1924-3 Tappi T494	l/md/sm q/cd/st	6700 2700
Berstfestigkeit-Mullen [kPa] burst strength résistance à l'éclatement	ISO 2758 Tappi T403	rel.	62 2,6
Aschegehalt [%] ash content taux de cendres	ISO 2144 Tappi T211		35-40
Wasseraufnahme-Cobb60 [g/m ²] Water absorbency Absorption capillaire	ISO 535 Tappi T441		<23
Naßfestigkeit [%] wet strength REH	optional optional ptionnel	ISO 3781	>20
Rohstoffbasis raw material base base de matières premières	100% recycelte Fasern /recycled fibres /fibres recyclées		

Toleranz +/-10% wenn nicht anders vermerkt / 10% unless otherwise noted / 10% sauf indication contraire
 tolerance
 tolérance

Validity of this specification - up to one year from date of issue.
 Date of issue Thursday, 5 November 2020

