

# Chantaffiche™ 200 JE ES

Durchleuchtungspapier entwickelt für den Druck mit Eco-Solvent Druckfarben |  
Backlit Paper designed for printing with Eco-Solvent inks

Technisches Datenblatt | Technical data sheet

Flächenbezogene Masse:  
Grammage: 150 g/m<sup>2</sup>

Ident-Nr.: 712452

Version: 01/2021

	Eigenschaft Characteristic	Methode Method	Einheit Unit	Typischer Wert Typical value	Toleranz Tolerance
1	Flächenbezogene Masse Grammage	DIN EN ISO 536	g/m <sup>2</sup>	150	± 6
2	Dicke Thickness	DIN EN ISO 534	µm	180	± 10
3	CIE Weißgrad CIE Whiteness	ISO 11475	%	98	± 5
4	Tensile Index längs Tensile Index MD	DIN EN ISO 1924		45	± 5
5	Tensile Index quer Tensile Index CD	DIN EN ISO 1924		25	± 5
6	Glanz OS Gloss ts	EN ISO 8254-1	%	22	± 3
7	Rauigkeit nach PPS Roughness PPS	DIN ISO 8791-4	µm	1.4	± 0.3

**Kontakt / Contact:****KÄMMERER Paper GmbH**

Römereschstraße 33

Phone +49 541 604-385

Elke.Tilch@kaemmerer-paper.com

D-49090 Osnabrück

[www.kaemmerer-paper.com](http://www.kaemmerer-paper.com)

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as KÄMMERER Paper GmbH deems appropriate. Refer to [www.kaemmerer-paper.com](http://www.kaemmerer-paper.com) for contact information.