

TECHNICAL DATA

MESH AMX5

Item	Unit	Value		Test Method
Base Fabric	Denier	1000DX1000D		(High tenacity yarn) 100%PES
Construction	Weaving/inch	12X12		/
Weight of MESH	Gsm/m2	270 +/- 20		DIN53352 BS3424 Method5B
Weight of pvc liner	Gsm/m2	/		DIN53352 BS3424 Method5B
Total weight	Gsm/m2	270 +/- 20		DIN53352 BS3424 Method5A
Width	cm	Up to 500		/
Tensile Strength	N/5cm	Warp	1250	DIN53352 BS3424
		Weft	1100	
Tearing Strength	N	Warp	235	DIN53356 BS3424
		Weft	225	
Air permeability	mm/s	2649		GB/T 2410-2008
Light transmission	/	37%		GB/T 5453-1997
Temperature Resistance	℃	—20～70		DIN53357 BS3425 Method10
Lacquering	\			
Flammability	\			
LOW CADMIUM & HEAVY METALS	\			
Conclusions and Announcements	Declaration by GLP: Please choose GLP products suitably according to relative provisions or industrial standards. GLP bears the responsibility for the specified technical and performance data on this page only. GLP is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)			