



# Verlatex Airtricot FR

Soluții pentru publicitate și decor

## BRIEF DESCRIPTION

- 100% polyester soft textured mesh with semi glossy finish
- Perfect double penetration after Dye-sub printing

## FEATURES



## INK PRINTABILITY



## MATERIAL DETAILS

Properties	Teste method	Metric	Imperial
Total Weight	DIN EN ISO 2286-2, ASTM D751	115 g/sq.m	3.4 oz/sq.yd
Base Fabric	DIN 60001, ASTM D7641	100%polyester	100%polyester
Weave Method	N/A	Warp-knitted	
Shrinkage	210 °C, 30s	≤2%	
Flame Resistance	DIN 4102-1-B1, NFPA 701 Test1 EN13501-1	IN 4102-1-B1, NFPA 701 Test1 EN13501-1	
Recommend Fixation Temperature	N/A	190°C - 210 °C, 1-2min	
Yellowing Temperature	SUPRKC REX-C400, 30s	≥210°C	
Width Available	DIN EN ISO 3759, ASTM D751-2006	Max 320 cm	126"
Standard Length	DIN EN ISO 3759, ASTM D751-2006	100m	110yds

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All of the Information above shall only be used as a guide; buyers shall independently test and determine the product's suitability. The mentioned data is available as test results and should not be used for the purpose of a lawsuit or warranty.

