



Tapet Art HT 160 FR

resistance and excellent dimensional stability.

SUBSTRATE

- Textured matte PVC, soft calendered, made from polymeric resins.

Finish	Textured: Marroco, Woodgrain, Pumice, Canvas		
	<i>Value</i>	<i>Tolerance</i>	<i>Standard</i>
Thickness (µm)	160 - Fire Retardant	± 10%	ASTM D 1593
Weight (g/m ²)	200 - 235	± 10%	ASTM D 1593
Fire Behavior (FR)	B s1 / d0		ISO 13501-1 / ISO 11925-2

ADHESIVE

- Clear acrylic based, permanent high tack

	<i>Value</i>	<i>Standard</i>
Peel Adhesion steel 20 min (N/25mm)	> 15	FINAT FTM1
Peel Adhesion steel 24 h (N/25mm)	> 25	FINAT FTM1
Shrinkage (mm)	Máx. 1	FINAT FTM 14
Application temperature (°C)	> 10	
Service temperature (°C)	-10 a 70	

LINER

- Double side PE

	<i>Value</i>	<i>Tolerance</i>	<i>Standard</i>
Thickness (µm)	130	± 10%	ISO 534
Weight (g/sqm)	135	± 10%	ISO 536

Tapet Art HT 160 FR

DURABILITY

- DURABILITY: up to 5 years (unprocessed and when applied under vertical exposure – normal Central European climate).
- Shelf Life: 24 months from the date of manufacture, applicable only to material that has not been processed, and stored according to the following conditions:
 - This material must be stored at a temperature of $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ and $50\% \pm 5\%$ relative humidity, without major climate deviations.
 - The storage area must be dry and clean.
 - Keep the material in the original package when not in use, in order to protect it from dust and contamination.
 - Do not expose to direct sunlight or heat sources.
 - The product must be stored vertically, so that its quality is not compromised.

PRINTING METHODS

- Specially developed for solvent, latex and UV large format printing.
- This product must be protected with the recommended lamination in order to provide the necessary strength.

- An excessive quantity of ink in the product will result in changes in its characteristics, in inappropriate drying, lamination detachment and / or poor product performance.

of the material's performance. Given the roughness of the material, a minimum drying period of 120 hours is recommended, in an environment with controlled temperature and humidity (we recommend a temperature between $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ and humidity of $50 \pm 5\%$) before any additional processing. Drying should be done with the product unrolled.

APPLICATION

surfaces with degraded paint.

- Do not expose to combustible vapors or spills.
- Surfaces on which the material will be applied must be carefully cleaned and free of dust, grease or any

before it is used.

IMPORTANT REMARKS

- Decal is not responsible for the ease or speed of removal of the applied material. It is necessary to have into account the appropriate air and substrate temperatures.

- We recommend that, to carry out a job, the same batch of product is used.
- The data provided in this information is based on our knowledge and experience. It is intended to be a source of information and is not a guarantee. It can be subject to change without previous notice.
- Decal is not responsible for misuse or improper storage, never being responsible for loss or damage to third parties.