

Film APET Clear GTB 300

Film Transparent optical clear, 300 microni

PROPERTIES	STANDARD	VALUE	UNIT	REMARKS
Thickness	ASTM D 1593	300	μ	Tolerance ± 7%
Density	ASTM D 792	1,34	g/cm ³	
Gloss 60°		>140	%	
Surface tension	ASTM D 2578-84	≥ 38	dyne/cm	
Tensile strength	ASTM D 638	~40	N/mm ²	
Shrinkage Machine direction (MD) Transversal direction (TD)	ASTM D 1204	≤ 5 ≤ 3	%	
Minimum sheet size		200X200	mm	Tolerance ± 1 mm
Maximum sheet size		1200X1600		
Reel width		MAX 1700	mm	Tolerance - 0 / +3mm
Storage	Store for at least 24 hours in the room where the material is processed. Do not expose to direct sunlight. Storage temperature ranging between 10 and 35°C Store rolls in original packaging.			